

TECHNICAL DATASHEET

Product Name: **Prepolymer BRISONATE 6689**

General Properties and Applications:

PREPOLYMER BRISONATE 6689 is based on Diphenylmethane-4,4'-diisocyanate and to be used with formulated polyester polyols for the production of Open slippers, sandals and medium density unit-soles for sandals. Prepolymer is viscous liquid at room temperature.

Provisional Specifications:

Property	Units	Specifications	Test Method
Colour		Yellowish	ASTM D4877
NCO Value	%	19.5±0.3	ASTM D5155
Viscosity @ 40°C	CPS	1000±200	ASTM D4878
Density @ 20°C	Kg/m ³	Approx. 1.2	ASTM D4659

Sampling:

Material must be homogenized prior to taking samples, moisture ingress must be prevented.

Packaging: 240 kg close top drums

Storage & Shelf life:

Store in well ventilated cool and dry place, away from direct sun light, rain and water. **PREPOLYMER BRISONATE 6689** reacts with moisture therefore moisture ingress must be prevented. Prepolymer becomes solid below 10°C, Ideal storage temperature is 22-30°C. In case material is solid , it can be re-melted by keeping it in air circulated heating oven at 70-80°C for about 12-18 hours; melted material should then be stored at recommended temperature. Shelf life of the product is around six months from date of manufacture if stored in tightly sealed drum at recommended temperature.

Vivan Inc General Trading L.L.C.

Corporate Address: Office No 1515, Park Lane Tower, P.O. Box No. 87556, Business Bay, Dubai, UAE

Phone: +97145668994 / +971524874459/ +971502844855

Email: info@vivaninc.com website: www.vivaninc.com